



ALLIAGES

ACIERS RÉSISTANTS AUX HAUTES TEMPÉRATURES

	CATEGORY	NUMBER	CAST EN / NF A	CAST ASTM	CAST UNS	WROUGHT GRADE AND ®
	Fe - Cr - Ni	1.4832	GX25CrNiSi20-14	/	/	/
	Fe - Cr - Ni	/	/	A297 HF	/	AISI 302
	Fe - Cr - Ni	1.4837	GX40CrNiSi25-12	A297 HH	/	AISI 309
	Fe - Cr - Ni	1.4840	GX15CrNi25-20	A351 - A743 CK20	J94202	AISI 310S
	Fe - Cr - Ni	1.4848	GX40CrNiSi25-20	A297 HK / A351 HK 40	J94224 / J94204	AISI 310
	Fe - Cr - Ni	1.4855	GX40CrNiSiNb24-24	/	/	/
	Fe - Ni - Cr	1.4805	GX35NiCrSi25-21	/	/	/
	Fe - Ni - Cr	1.4806	GX40NiCrSi35-17	/	/	/
	Fe - Ni - Cr	1.4807	GX40NiCrSiNb35-18	/	/	/
	Fe - Ni - Cr	/	/	A297 HN	J94213	/
	Fe - Ni - Cr	1.4859	GX10NiCrSiNb32-20	A351 - A743 CT15C	N08151	INCOLOY 800H ®
	Fe - Ni - Cr	Sambralloy 800H	/	/	N08151	Incoloy 800 H ®
	Ni - Cr - W	/	GX45NiCrW45-25 M	/	/	/
	Ni - Cr - W	/	GX50NiCrW45-35-11	/	/	/
	Ni - Cr	/	C-NiCr15Fe AT1	A494 CY40	N06040	Inconel 600 ®
	Ni - Cr - Nb	2.4680	GNiCr50Nb	A560 50 Cr-50 Ni -Cb	R20501	/
	Co - Cr	2.4778	GCoCr28	/	/	UMCo 50 ®
	Co - Cr - Nb	2.4779	GCoCr28Nb	/	/	UMCo 51 ®

© 2016

Acierie et fonderie Haute Sambre
rue du pont des moines
59145 Berlaimont - France
Tel +33(0)3.27.67.39.00
fax +33(0)3.27.53.61.83
acieriefonderiehautesambre.com