



ALLOYS

CARBON & ALLOY STEELS

CATEGORY	NUMBER	CAST EN / NF A	CAST ASTM	CAST UNS
Fe	/	GE230 N	A 216 WCB / WCC	J03002 / J02503
Fe	1.0455	GS240 N	A 216 WCB / WCC	J03002 / J02503
Fe	/	GE280 N	A 216 WCB / WCC	J03002 / J02503
Fe	/	GE320 N	/	/
Fe	/	GE370 N	/	/
Fe	1.0619	GP240GH N / QT	A216 WCB	J03002
Fe			A352 LCB	J03003
Fe	1.0625	GP280GH N / QT	A216 WCC	J02503
Fe			A352 LCC	J02505
Fe	1.6220	G20Mn 5 N / QT	A216 WCC	J02503
Fe			A352 LCC	J02505
Fe - Mo	1.5419 QT	G20Mo5 QT	A 352 LC1	J12522
Fe - Ni	1.5636 QT	G9Ni10 QT	A352 LC2	J22500
Fe - Ni	1.5638 QT	G9Ni14 QT	A352 LC3	J31550
Fe - Ni	1.5681 QT	GX9Ni5 QT	A352 LC4	J41500
Fe - Ni	/	/	A352 LC9	J31300
Fe - Cr - Mo	1.7357 QT	G17CrMo5-5 QT	A 217 WC6	J12072
Fe - Cr - Mo	1.7379 QT	G17CrMo9-10 QT	A 217 WC9	J21890
Fe - Cr - Mo	1.7365 QT	GX15CrMo5 QT	A217 C5	J42045
Fe - Cr - Mo	1.7221 QT	G26CrMo4 QT	/	/
Fe - Cr - Mo	1.7230 QT	G35CrMo4 QT	/	/
Fe - Cr - Mo	1.7231 QT	G42CrMo4 QT	/	/
Fe - Cr - Mo - V	/	/	A217 C12A	J84090
Fe - Cr - Mo - V	1.7706 QT	G17CrMoV5-10 QT	/	/
Fe - Ni - Cr - Mo	1.6771 QT	G30NiCrMo14 QT	/	/
Fe - Ni - Cr - Mo	1.6570 QT	G32NiCrMo8-5-4 QT	/	/

© 2016

Acierie et fonderie Haute Sambre
rue du pont des moines
59145 Berlaimont - France
Tel +33(0)3.27.67.39.00
fax +33(0)3.27.53.61.83
acieriefonderiehautesambre.com