



ALLOYS

NICKEL & COBALT BASIS

CATEGORY	NUMBER	CAST EN / NF A	CAST ASTM	CAST UNS	WROUGHT GRADE AND ®
Ni - Cr	2.4816	C-NiCr15Fe AT1	A494 CY40	N06040	Inconel 600 ®
Ni - Cr - Mo	2.4607	NiCr23Mo16Al	A494 CX2M	N06059	Alloy 59 ®
Ni - Cr - Mo	2.4686	C-NiCr16Mo16 AT	A494 CW2M	N26455	Hastelloy C4 ®
Ni - Cr - Mo	2.4858	C-NiFe30Cr20Mo3CuNb	A494 CU5MCuC	N08826	Incoloy 825 ®
Ni - Cr - Mo	Sambralloloy 59	NiCr23Mo16Al	A494 CX2M	N06059	Microfer 5923hMo ®
Ni - Cr - Mo - Nb	2.4856	C-NiCr22Mo9Nb4 AT	A494 CW6MC	N26625	Inconel 625 ®
Ni - Cr - Mo - W	9.4602	C-NiCr21Mo14Fe4W3 AT	A494 CX2MW	N06022	Hastelloy C22 ®
Ni - Cr - Mo - W - Cu	/	/	/	N06030	Hastelloy G-30 ®
Ni - Mo	2.4617	C-NiMo31 AT	A494 N7M	N30007	/
Ni - Mo	2.4685	C-NiMo30Fe5 AT	A494 N12MV	N30012	Hastelloy B2 ®
Ni - Mo - Cr	Sambralloloy B3	/	/	N10675	Hastelloy B-3 ®
Ni - Mo - Cr - W	2.4883	C-NiMo17Cr16Fe6W4 AT	A494 CW-12MW	N30002	Hastelloy C276 ®
Ni	2.4170.01	C-Ni99, -HC	A494 CZ100	N08826	AISI CZ-100
Ni	Sambralloloy Ni36	/	/	/	Invar 36 ®
Ni - Cu	2.4365	C-NiCu30	A494 M35-1	N24135	Monel 400 ®
Ni - Cu - Nb	/	C-NiCu30Nb2Si2	A494 M30C	N24130	/
Ni - Co - Cr	Sambralloloy PER 101 F	G-NiCo14Cr10AlTiMo	/	/	/

© 2016

Acierie et fonderie Haute Sambre
rue du pont des moines
59145 Berlaimont - France
Tel +33(0)3.27.67.39.00
fax +33(0)3.27.53.61.83
acieriefonderiehautesambre.com